

A REVIEW OF CUMULATIVE DAMAGE
FOR FATIGUE COMMITTEE
OF THE STRUCTURES AND MATERIALS PANEL
ADVISORY GROUP FOR AERONAUTICAL RESEARCH AND DEVELOPMENT

By Herbert F. Hardrath

NASA Langley Research Center
Langley Station, Hampton, Va., U.S.A.

Presented at the Advisory Group for Aeronautical Research and Development

GPO PRICE \$ _____

CFSTI PRICE(S) \$ _____

Hard copy (HC) 1.00

Microfiche (MF) 50

ff 653 July 65

Munich, Germany
June 14, 1965

FACILITY FORM 602

N 65-33918
(ACCESSION NUMBER)

17
(PAGES)

TX-56449
(NASA CR OR TMX OR AD NUMBER)

(THRU)

1
(CODE)

32
(CATEGORY)

A REVIEW OF CUMULATIVE DAMAGE
FOR FATIGUE COMMITTEE
OF THE STRUCTURES AND MATERIALS PANEL
ADVISORY GROUP FOR AERONAUTICAL RESEARCH AND DEVELOPMENT
By Herbert F. Hardrath
NASA Langley Research Center

33918

The analysis of any practical fatigue problem almost invariably involves some consideration of the progressive accumulation of damage due to loads that vary in amplitude. It is the purpose of this paper to review the current state of the art of such analysis and to make recommendations for future action.

Advance copies of the review were submitted to other members of the Fatigue Committee and their associates for comment. The writer gratefully acknowledges their contributions and several of these have been included in the present version of the report.

Author

A bibliography of papers on cumulative damage published by NASA, NLR, DVL, and LBF is appended.

HISTORICAL BACKGROUND

The majority of fatigue tests, both constant and variable amplitude, that have been performed during the many years that fatigue has been studied have been of the rotating-beam type. In a large percentage of these investigations, carefully polished smooth specimens were employed.

Some 40 years ago, Palmgren (ref. 1) proposed a form of cumulative damage relationship that ultimately led to what is now referred to as the Miner (sometimes Palmgren-Miner) relationship (ref. 2). This relation is based upon the simple concept that "damage" accumulates linearly with cycle-ratio and failure occurs when the accumulated damage or sum of cycle ratios reaches unit ($\sum \frac{n}{N} = 1$).

The linear rule of cumulative damage has been used extensively in spite of the fact that a large number of investigations have "proved it wrong". Early evidence that $\sum \frac{n}{N} \neq 1$ was gained in rotating-beam tests employing simple two-level load schedules. Generally, investigations found that if the stress level was changed from a high to a lower value the summation of cycle ratios was less than unity. Conversely, a sum greater than one was frequently observed when the stress level was increased during a test. These observations led to a great deal of speculation regarding the effects of overstressing, understressing, and coaxing.

Very probably some of the apparent inconsistency in the value of $\sum \frac{n}{N}$ achieved in a given set of tests is due to inaccuracies in the S-N curves used to perform the calculations.

Some of the investigators proposed relations of their own (refs. 3-16). Generally, these relations involve certain linear or non-linear weighting factors on the cycle ratios employed by Palmgren and Miner. A few have the added feature that the S-N curve is progressively modified to account for the systematic depletion of life and of the fatigue strength remaining in the specimen. All are essentially empirical relations. Some of the authors have claimed superiority of their procedures over the linear method, but this superiority is usually achieved by adjusting empirical constants to suit the data under consideration. Few of the relations proposed attempt to account for the actual mechanisms of damage.

An objective comparison between test results taken from the literature and predictions made by the various cumulative damage methods has been made by the Lockheed Aircraft Company (ref. 17). These investigators concluded that the linear cumulative damage theory gave estimates of fatigue life that were more nearly correct in more cases than were estimates made by any other method evaluated. No trend was evident that any estimation procedure was superior to the linear method for any class of test results.

Thus, the linear method appears attractive because of its simplicity and general superiority, at least for preliminary estimates. Significant discrepancies between observed life and predicted life are, of course, common.

CURRENT STUDIES

Parameters in Experimental Studies

More recently, several new parameters have been introduced in order to more adequately simulate service or design problems. Among these are:

1. More complex loading schedules have been used since they were made possible by the development of automatic programming equipment.
2. Axially-loaded specimens were employed.
3. Mean stresses, which could not be applied to rotating beams, became possible and were employed.
4. Specimens frequently incorporate structural joints or at least moderate stress concentrations.
5. A significant number of "research" fatigue tests have been conducted on full-scale structures in Australia, England, the United States and the Netherlands.

In practice, more and more ad hoc fatigue tests are being conducted with programs of loads simulating the expected service experience.

Phenomenological Trends

Among the systematic trends observed in many of these more recent tests are the following:

1. The fact that the linear summation of cycle ratios does not always equal one is rather universally accepted as a fact. However, the procedure is widely used as a tool for making estimates in design.

2. Systematic variations in $\sum \frac{n}{N}$ due to various parameters of test programs are being recognized and cataloged. For example:

a. $\sum \frac{n}{N}$ tends to be greater than one for tests in which a tensile mean stress is used, and increases with the mean stress. This observation suggests that $\sum \frac{n}{N} = 1$ yields estimates on the "safe side" for many practical problems. (Dr. Gassner advises that he and Dr. Jacoby have some unpublished data which show that $\sum \frac{n}{N}$ may be in error on the unsafe side by large margins even in cases where positive mean stresses were employed.)

b. $\sum \frac{n}{N}$ tends to be one or less for tests in which stresses are completely reversed.

c. The range of $\sum \frac{n}{N}$ values is smaller for complex loading schedules than was observed in the earlier overstressing and coaxing tests.

3. The sequence of loading employed in block tests may have a significant effect on fatigue life obtained. This observation dictates that caution be used in setting up fatigue tests for establishing the safe life of flight vehicles.

4. Tests conducted under a random sequence of loading frequently produce lives shorter than those observed in block tests for the same frequency distribution of loads.

5. Ground-air-ground and other negative load cycles can have a much more severe effect on life than was previously recognized or predicted from theories. Reductions in life by factors of 2 to 4 compared to similar tests without negative loads are common. The linear theory might predict only a few percent reduction in some of these cases.

6. High positive load cycles can improve resistance to failure under subsequent lower loads. This effect may be observed even after a crack is present in the structure.

7. On the other hand, once a crack is present, a sufficiently high load can produce catastrophic failure.

Significance of Crack Propagation

The role of cracks in the fatigue failure process is getting much more attention than heretofore. The presence of such cracks and their extent is the only measure of the total damage that has been accrued by a specimen or structural component. The rate at which such a crack propagates and the residual static strength for any crack length are the only reliable indices of the remaining longevity of the component in question.

In practical situations, visible fatigue cracks may be present for one-half or more of the total fatigue life. The fact that some microscopic crack growth has occurred before the crack becomes visible suggests that sub-microscopic cracks may be present in many parts before the parts are placed in service.

These considerations are being employed to develop rational methods for estimating life under variable-amplitude loading. The first analytical procedure proposed along these lines is that of Valluri (ref. 16). Valluri developed his expression from basic considerations of local plasticity, then through crack initiation, crack propagation and finally to failure. While this is a rational approach, its quantitative usefulness is subject to question because many of the observations listed earlier cannot be accounted for in the present form.

Significance of Residual Stresses

Many of the observations regarding the increase of $\sum \frac{n}{N}$ with mean stress, beneficial effect of high loads, deleterious effect of negative loads and sequence effects are being rationalized on the basis of residual stresses formed when the material near a stress raiser is plastically deformed. Fundamental studies are underway that will help to define these residual stresses and how they modify fatigue behavior (ref. 18).

To date, only the Smith method (ref. 7) attempts to account for the effects of residual stresses on cumulative damage. Although this method has a basically sound foundation, the assumptions made in the quantitative solution of a given problem appear primitive. It is quite possible that as additional detailed information regarding local plastic stresses becomes available, a method can be developed that will inspire more confidence.

Interpretation of Random Loadings

The interpretation of random time histories of loadings in terms of the fatigue damage that they produce is currently receiving increased attention. A wide variety of "counting schemes" by which time histories may be analyzed have been proposed (ref. 19). Unfortunately, analytical schemes for computing the statistics of the necessary quantities are not yet available. Power

spectral density procedures are widely acclaimed for treating random processes, but cannot be employed without a reliable quantitative theory of cumulative damage nor can they provide information on ranges of stress excursions and other parameters generally accepted as controlling fatigue behavior.

THE OUTLOOK FOR THE FUTURE

Future developments to improve the state of the art with respect to cumulative damage will probably include increased emphasis on the mechanisms involved, namely, crack propagation and failure at a level lower than the original strength of a component. Since fatigue in service is experienced as a result of loads that vary in a random sequence, more emphasis will be placed on tests that employ complex load histories. The systematic effects of residual stresses produced by large positive and negative loads will need to be taken into account, at least in principle.

It is most unlikely that a cumulative damage theory will be developed in the foreseeable future which will eliminate the need for considerable ad hoc testing to establish the adequacy of particular pieces of hardware. The most significant feature controlling fatigue behavior is, of course, the "quality" of the part itself. A truly formidable array of interacting parameters controls "quality". Among these are the material, its heat treatment and other processing details, the configuration, detailed stress distribution, interference fits, other residual stresses, fretting, flaws, etc. Until the influences of each of these parameters are also represented in the analytical treatment, a sophisticated and precise cumulative damage theory is probably not the greatest need of designers.

Actually, the efficiency of testing is probably improved by conducting program-load tests for the following reasons:

1. Every test provides direct information while several constant amplitude tests must be performed to provide at least a portion of an S-N curve.
2. Variable-amplitude tests are more likely to identify the probable location of failure.
3. Interpretation of results is less dependent upon analysis by a cumulative damage theory, particularly if the loads have been anticipated correctly.

This is not to say that research on cumulative damage is fruitless. A reasonably adequate cumulative damage rule is sorely needed in order to anticipate the way in which fatigue life may be affected by modifications in speed, gross-weight or mission without extensive retesting. (In military aircraft, such changes have modified the frequency of occurrence of a given load level per flight by two orders of magnitude.) Thus research on the problem must be continued vigorously, keeping in mind that the ultimate method must account for practical complexities in the loading sequence. However, procedures for accounting for the quality of the construction are also needed. In many cases ad hoc testing will be required to prove a given design.

Even if all the parameters controlling quality and cumulative damage could be handled analytically, the safety of a given aircraft in a fleet might still be jeopardized by failures initiated by inadvertent flaws or accidental damage. To insure against such failures, fail-safe construction and diligent inspection programs are and will remain necessary. The discussion of fail-safe design procedures is, of course, beyond the scope of this discussion.

RECOMMENDATIONS FOR AGARD ACTION

From the foregoing review and the attached bibliography, it is quite clear that the current trends in research on cumulative damage are likely to lead to significant contributions. In contrast to common practice in earlier studies, the practical complexities of both structure and load experience are receiving the proper emphasis. The national aeronautical research centers represented on the Fatigue Committee are taking leading roles in this effort and are generally agreed on the kinds of studies needed. The efforts of these groups complement each other in a rather remarkable way.

Thus, it is difficult to imagine that any new effort organized by AGARD on an international scale is either needed desperately or that it could be expected to lead to new breakthroughs. There is also considerable doubt that a new effort in this area is needed for mutual defense purposes.

One suggestion that might be helpful is that a close liaison be maintained among the research groups working in the various countries. Personal contacts are, of course, most desirable, and several exchanges of visits have taken place during the past several years. With international travel becoming more common, it is reasonable to expect that such visits will be more frequent in the future. AGARD might well encourage these mutual exchanges.

Dr. Schijve offered two specific proposals for possible consideration by the Fatigue Committee:

1. Compile a detailed review of procedures used by aircraft firms to prove the fatigue airworthiness of their designs.

2. Prepare periodic, critical reviews of current investigations on aeronautical fatigue to acquaint designers and other research workers with current advances on cumulative damage testing, random-load fatigue and the effects of residual stresses.

Expertly done, such reviews could be very useful.

REFERENCES

1. Palmgren, A.: Die Lebensdauer von Kugellagern, Z. Ver. Dtsch. Ing. 339-341 (1924).
2. Miner, M. A.: Cumulative Damage in Fatigue. Jour. Appl. Mech., vol 12, no. 3, Sept. 1945, pp. A-159 - A-164.
3. Lundberg, B.: Fatigue Life of Airplane Structures. Jour. Aero. Science, vol. 22, no. 6, pp. 349-402, June 1955.
4. Shanley, F. R.: A Theory of Fatigue Based on Unbonding During Reversed Slip. Rand Corp. Rpt. P-350-1, 11 Nov. 1952.
5. Langer, B. F.: Fatigue Failure from Stress Cycles of Varying Amplitude. Jour. Appl. Mech., vol. 4, pp. A-160 - A-162, Dec. 1937.
6. Grover, H. J.: Cumulative Damage Theories (In Proceedings of the Symposium on Fatigue of Aircraft Structures), WADC Technical Rpt. 59-507, pp. 207-225, Aug. 1959.
7. Smith, C. R.: Prediction of Fatigue Failures in Aluminum Alloy Structures. SESA Proceedings, vol. 12, no. 2, pp. 21-28, 1955.
8. Henry, D. L.: A Theory of Fatigue-Damage Accumulation in Steel. ASME Trans., vol. 77, no. 6, pp. 913-918, Aug. 1955.
9. Corten, H. T., and Dolan, T. J.: Cumulative Fatigue Damage. Session 3, Paper 2, Proceedings of the International Conference on Fatigue of Metals of the IME, London, 10-14 Sept. 1956, and at the ASME, New York, 28-30 Nov. 1956.
10. Kommers, J. B.: The Effect of Overstress in Fatigue on the Endurance Life of Steel. ASTM Proceedings, vol. 45, pp. 532-541, 1945.
11. Richart, F. E., Jr., and Newmark, N. M.: A Hypothesis for the Determination of Cumulative Damage in Fatigue. ASTM Proceedings, vol. 48, pp. 767-798, 1948.
12. Marco, S.M. and Starkey, W. L.: A Concept of Fatigue Damage. ASME Trans., vol. 76, no. 4, pp. 627-632, May 1954.
13. Freudenthal, A. M., and Heller, R. A.: On Stress Interaction in Fatigue and a Cumulative Damage Rule - Part 1 - 2024 Aluminum and SAE 4340 Steel Alloys. WADC Tech. Rpt. 58-69-Pt. 1, June 1958.
14. Levy, J. C.: Cumulative Damage in Fatigue - A Design Method Based on the S-N Curves. Jour. Royal Aero. Soc., vol. 61, no. 559, pp. 485-491, Jul. 1957.

15. Fuller, J. R.: Cumulative Fatigue Damage Due to Variable-Cycle Loading. Noise Control, July-August, 1961.
16. Valluri, S. R.: A Theory of Cumulative Damage in Fatigue. Galcit SM 61-2, Douglas Aircraft Co., Revised Oct. 1961.
17. Crichlow, W. J.; McCulloch, A. J.; Young, L. and Melcon, M. A.: An Engineering Evaluation of Methods for the Prediction of Fatigue Life in Airframe Structures, Tech. Rept. ASD-TR-61-434, Mar. 1962.
18. Crews, John H., Jr., and Hardrath, Herbert F.: A Study of Cyclic Plastic Stresses at a Notch Root. Presented at May 5-7, 1965 meeting of Society for Experimental Stress Analysis in Denver, Colorado.
19. Schijve, J.: The Analysis of Random Load-Time Histories With Relation to Fatigue Tests and Life Calculations. Fatigue of Aircraft Structures, W. Barrois and E. L. Ripley, eds., The Macmillan Co., 1963, pp. 115-149.

BIBLIOGRAPHY

NASA, Langley Research Center

- Hardrath, Herbert F., and Utley, Elmer C., Jr.: An Experimental Investigation of the Behavior of 24S-T4 Aluminum Alloy Subjected to Repeated Stresses of Constant and Varying Amplitudes. NACA TN 2798, Oct. 1952.
- Whaley, Richard E.: Fatigue Investigation of Full-Scale Transport-Airplane Wings - Variable-Amplitude Tests With a Gust-Loads Spectrum. NACA TN 4132, Nov. 1957.
- Huston, Wilber B.: Comparison of Constant-Level and Randomized-Step Tests of Full-Scale Structures as Indicators of Fatigue-Critical Components. Symposium on Full-Scale Fatigue Testing of Aircraft Structures, Amsterdam, Holland, June 1959.
- Huston, Wilber B., and Ward, John F.: Evaluation of Fatigue Sensitive Areas and Cumulative Damage in Full-Scale Fatigue Testing. United States Air Force Symposium on Fatigue of Aircraft Structures, Dayton, Ohio, Aug. 1959.
- Fralich, Robert W.: Experimental Investigation of Effects of Random Loading on the Fatigue Life of Notched Cantilever - Beam Specimens of 7075-T6 Aluminum Alloy. NASA Memo 4-12-59L, June 1959.
- Hardrath, Herbert F., and Naumann, Eugene C.: Variable-Amplitude Fatigue Tests of Aluminum-Alloy Specimens. American Society for Testing Materials, San Francisco, California. ASTM Special Technical Publication No. 274, Oct. 1959.
- Naumann, Eugene C.; Hardrath, Herbert F., and Guthrie, David E.: Axial-Load Fatigue Tests of 2024-T3 and 7075-T6 Aluminum Alloy Sheet Specimens Under Constant- and Variable-Amplitude Loads. NASA TN D-212, Dec. 1959.
- Hardrath, Herbert F.; Utley, Elmer C. and Guthrie, David E.: Rotating-Beam Fatigue Tests of Notched and Unnotched 7075-T6 Aluminum-Alloy Specimens Under Stresses of Constant and Varying Amplitudes. NASA TN D-210, Dec. 1959.
- Foster, Lee R., Jr., and Whaley, Richard E.: Fatigue Investigation of Full-Scale Transport-Airplane Wings; Tests with Constant-Amplitude and Variable-Amplitude Loading Schedules. NASA TN D-547, Oct. 1960.
- Fralich, Robert W.: Experimental Investigation of Effects of Random Loading of the Fatigue Life of Notched Cantilever-Beam Specimens of SAE 4130 Normalized Steel. NASA TN D-663, Feb. 1961.
- Hudson, C. Michael and Hardrath, Herbert F.: Effects of Changing Stress Amplitude on the Rate of Fatigue-Crack Propagation in Two Aluminum Alloys. NASA TN D-960, Sept. 1961.

- Naumann, Eugene C., and Schott, Russell L.: Axial-Load Fatigue Tests Using Loading Schedules Based on Maneuver-Load Statistics. NASA TN D-1253, May 1962.
- Naumann, Eugene C.: Variable-Amplitude Fatigue Tests with Particular Attention to the Effects of High and Low Loads. NASA TN D-1522, Dec. 1962.
- Hardrath, Herbert F.: Crack Propagation and Final Failure. Materials Research and Standards, vol. 3, no. 2, Feb. 1963.
- Leybold, Herbert A., and Naumann, Eugene C.: A Study of Fatigue Life Under Random Loading, 66th Annual Meeting of the American Society for Testing Materials, Atlantic City, New Jersey, June 23-28, 1963.
- Hudson, C. Michael and Hardrath, Herbert F.: Investigation of the Effects of Variable-Amplitude Loadings on Fatigue Crack Propagation Patterns. NASA TN D-1803, Aug. 1963.
- Hardrath, Herbert F.: Cumulative Damage. Presented at the Tenth Sagamore Army Materials Conference "Fatigue - An Interdisciplinary Approach", Sagamore, New York, Aug. 13-16, 1963.
- Naumann, Eugene C.: Evaluation of the Influence of Load Randomization and of Ground-Air-Ground Cycles on Fatigue Life. NASA TN D-1584, Oct. 1964.
- Crews, John H., Jr., and Hardrath, Herbert F.: A Study of Cyclic Plastic Stresses at a Notch Root. Presented at SESA Meeting May 5-7, 1965, in Denver, Colorado.
- Naumann, Eugene C.: Fatigue Under Random and Programmed Loads. NASA TN D-2629, Feb. 1965.
- Leybold, Herbert A.: Techniques for Examining the Statistical and Power Spectral Properties of Random Time Histories. NASA TN D-2714, Mar. 1965.

Nationaal Lucht- en Ruimtevaartlaboratorium

Amsterdam

- Hartman, A.: Preliminary Investigation to Verify the Cumulative Damage Hypothesis $\sum n/N = 1$ on Riveted Joints. NLR Report M.1923, 1953.
- Schijve, J. and Jacobs, F. A.: Fatigue Tests on Notched and Unnotched Clad 24 S-T Sheet Specimens to Verify the Cumulative Damage Hypothesis. NLR Report M.1982, April 1955.
- Plantema, F. J.: Some Investigations on Cumulative Damage. Colloquium on Fatigue, Stockholm 1955. Springer Verlag, 1956, p. 218.
- Schijve, J. and Jacobs, F. A.: Research on Cumulative Damage in Fatigue of Riveted Aluminum Alloy Joints. NLR Report M.1999, Jan. 1956.
- Schijve, J.: Critical Analysis of the Fatigue Damage Concept and Some Consequences for Fatigue Testing of Aircraft Structures. Minutes of the 4th Conference of the ICAF, Zurich, 1956, p. 36.
- Schijve, J. and Jacobs, F. A.: Program-Fatigue Tests on Notched Light Alloy Specimens of 2024 and 7075 Material. NLR Report M.2070, Mar. 1960.
- Schijve, J.: The Endurance Under Program-Fatigue Testing. Symposium on Full-Scale Fatigue Testing of Aircraft Structures, Amsterdam 1959. Pergamon Press, 1961, p. 41. Also: NLR Report MP.178.
- Schijve, J.: Fatigue Crack Propagation in Light Alloy Sheet Material and Structures. Advances in Aeronautical Sciences, vol. 3, Pergamon Press, 1961, p. 387. Also: NLR Report MP.195.
- Schijve, J.; Broek, D. and de Rijk, P.: Fatigue-Crack Propagation Under Variable-Amplitude Loading. NLR Report M.2094, Jan. 1961.
- Schijve, J.: The Analysis of Random Load-Time Histories With Relation to Fatigue Tests and Life Calculations. Symposium on Fatigue of Aircraft Structures, Paris 1961. Pergamon Press, 1963, p. 115. Also: NLR Report MP.201.
- Schijve, J. and Broek, D.: Crack Propagation Under Variable-Amplitude Loading. Aircraft Engineering, Nov. 1962, vol. 34, p. 314. Also: NLR Report MP.208.
- Schijve, J.: Estimation of Fatigue Performance of Aircraft Structures. Symposium on Fatigue of Aircraft Structures. ASTM Special Technical Publication No. 338, 1962, p. 193. Also: NLR Report MP.212.
- Schijve, J.: Fatigue Life and Crack Propagation Under Random and Programmed Load Sequences. Symposium on Current Aeronautical Fatigue Problems, Rome 1963. Pergamon 1965, p. 403. Report MP.219, Apr. 1963.

Schijve, J.: Analysis of the Fatigue Phenomenon in Aluminum Alloys. NLR Report M.2122, July 1964.

Schijve, J. and de Rijk, P.: Fatigue Lives Obtained in Random and Program Tests on Full-Scale Wing Center Sections. NLR Report S.611, Dec. 1963.

Schijve, J. and Jacobs, F. A.: Programme-Fatigue Tests on Aluminum Alloy Lug Specimens With Slotted Holes and Expanded Holes. NLR Report M.2139, Nov. 1964.

Schijve, J. and Broek, D.: Fatigue Test Results of Two-Full-Scale Wing Center Sections Under Ground-to-Air Cycle Loading. NLR Report S.635, April 1965.

Laboratorium für Betriebsfestigkeit
and
Deutschen Versuchsanstalt für Luftfahrt
Germany

- Gassner, E.: Festigkeitsversuche mit wiederholter Beanspruchung im Flugzeugbau. Luftwissen 6 Nr. 2, S.61-64, 1939.
- Gassner, E.: Über bisherige Ergebnisse aus Festigkeitsversuchen im Sinne der Betriebsstatistik. Bericht 106, I. Teil, Lilienthal-Gesellschaft für Luftfahrtforschung, S.9-14, Jan. 1939.
- Gassner, E.: Auswirkung betriebsähnlicher Belastungsfolgen auf die Festigkeit von Flugzeugbauteilen. Jahrbuch der Deutschen Luftfahrtforschung, S.1972-983, 1941.
- Gassner, E.: Ergebnisse aus Betriebsfestigkeits-Versuchen mit Stahl- und Leichtmetallbauteilen. Bericht 152, Lilienthal-Gesellschaft für Luftfahrtforschung S.13-23, Aug. 1942.
- Gassner, E.: Zur Aufstellung von Bemessungsregeln für Flugzeugbauteile. Jahrbuch der Deutschen Luftfahrtforschung, 1944.
- Gassner, E.; Luttner, A.: Betriebsfestigkeit von langgeschweissten Flachstaben aus Chrom-Vanadin-Stahl. DVL-Bericht UM 1344 (17.9 1944) (Auszug in: Techn. Ber. der ZWB 11, 1944)
- Gassner, E.; Luttner, A.: Betriebsfestigkeits-Versuche mit Widerstands-Abtrenn-Schweisverbindungen aus Chrom-Vanadin-Stahl. DVL-Bericht UM 1385 (15.11.1944) Auszug in: Techn. Ber. der ZWB 11 (1944)
- Gassner, E.: Einfluss von Bohrungsoberfläche und Bolzenpassung auf die Betriebsfestigkeit von Flachgurten. Techn. Ber. der ZWB 11 (1944)
- Gassner, E.; Teichmann, A.: Zur Betriebsfestigkeit gekerbter Bauteile Techn. Ber. der ZWB 11 (1944)
- Teichmann, A.; Gassner, E.: Betriebsfestigkeit eines Laschenstosses mit nichtgepassten Schraubenbolzen. Techn. Ber. der ZWB 12 (1945)
- Gassner, E.; Teichmann, A.: Ansatz und Durchführung von Betriebsfestigkeits-Versuchen. Techn. Ber. der ZWB 12 (1945)
- Gassner, E.: Strength Investigations in Aircraft Construction Under Repeated Application of the Load. NACA TM 1087 (1946).
- Gassner, E.: Preliminary Results from Fatigue Tests with Reference to Operational Statistics. NACA TM 1266 (1950).

- Bautz, W.: Untersuchungen über die Schadenslinie bei Leichtmetallen.
VDI-Z. 84, S. 918-919 (1940)
- Bautz, W.: Kritik der Dauerfestigkeit als Bemessungsgrundlage. Forsch.
Ing.-Wes. S. 161-166 (1941)
- Bautz, W.; Gassner, W.; Svenson, O.: Beanspruchungsmessungen und Betriebsfestig-
keits-Versuche an Fahrzeug-Bauteilen. ATZ 53, Nr. 11, S. 286/287, (1951)
- Gassner, E.: Betriebsfestigkeit, eine Bemessungsgrundlage für
Konstruktionsteile mit statistisch wechselnden Betriebsbeanspruchungen
Konstruktion 6, Nr. 3, S. 97-104 (1954)
- Gassner, E.: Zur Frage der Ermüdungsfestigkeit im Flugzeugbau. Jahrbuch
der WGL, S. 286-294 1954
- Gassner, E.: Effect of Variable Load and Cumulative Damage of Fatigue
in Vehicle and Airplane Structures. In: Proceedings of the International
Conference on Fatigue of Metals, London-New York (1956), S. 304-309
Hrsg. von der Institution of Mechanical Engineers, London 1956
- Gassner, E.: The Problem of Fatigue Strength in Aircraft Structures. Aircraft
Engineering, XXVIII, Nr. 329, S. 228-234 (1956)
- Gassner, E.: Ermüdungsfestigkeit bei statistisch veränderlichen
Spannungsamplituden. In: Kolloquium über Ermüdungsfestigkeit Hrsg. von
Weibull, W. u. Odqvist, F.K.G., Stockholm 1955. S. 63-65, Springer-Verlag,
Berlin, Göttingen, Heidelberg 1956
- Gassner, E.: Performance Fatigue Testing with Respect to Aircraft Design.
In: Fatigue in Aircraft Structures. Ed. by Freudenthal, A.M., New York
1956. S. 178-206, Academic Press Inc. New York 1956
- Bautz, W.: Gestaltfestigkeit bei dynamischer Beanspruchung, Wege zu ihrer
Erhöhung durch konstruktive und fertigungstechnische Massnahmen.
VDI-Berichte Bd. 28, S. 35-42 (1958)
- Gassner, E.: Review of Investigation on Aeronautical Fatigue in Western
Germany. In: Minutes of the 6th ICAF-Conference, Amsterdam 1959,
Hrsg. vom Nationaal Aeronautical Research Institute, Amsterdam 1959.
- Bautz, W.; Gassner, E.; Svenson, O.: Betriebsfestigkeit. In: Beispiele
angewandter Forschung 1959, Hrsg. von der Fraunhofer-Gesellschaft zur
Förderung der angewandten Forschung e.V., München 1959
- Gassner, E.; Horstmann, K.F.: Einfluss des Start-Lande-Lastwechsels auf die
Lebensdauer von beanspruchter Flügel von Verkehrsflugzeugen. In: Advances
in Aeronautical Sciences, Proceedings of the 2nd International Congress in
the Aeronautical Sciences Zurich 1960, Hrsg. von Th. von Karman, Pergamon
Press, Oxford, London, New York, Paris, 1962, Vol. 4, S. 763-780.

- Gassner, E.; Schutz, W.: The Significance of Constant Load Amplitude Tests for the Fatigue Evaluation of Aircraft Structures. In: Full Scale Fatigue Testing of Aircraft Structures, Proceedings of the ICAF-Symposium, Amsterdam 1959, S.14-40, Ed. by Plantema F.J.u. Schijve, J., Pergamon Press, Oxford, London, New York, Paris, 1961
- Gassner, E.; Svenson, O.: Einfluss von Storschwingungen auf die Ermüdungsfestigkeit. Stahl und Eisen 82, Nr. 5, S.276-282, (1962)
- Gassner, E.; Schutz, W.: Evaluating Vital Vehicle Components by Programme Fatigue Tests. In: Proceedings of the Ninth International Automobile Technical Congress, London 1962. Ed. by Eley, G., The Institution of Mechanical Engineers, London (1962), S. 195-205
- Gassner, E.: On the Influence of Fretting Corrosion on the Fatigue Life of Notched Specimens of an AlCuMg 2 Alloy. In: Proceedings of the Ninth ICAF-AGARD-Symposium, Paris 1961, Ed. by Barrois, W.u. Ripley, E.L., Pergamon Press, London, Oxford, New York, Paris, S. 87-95 (1963)
- Gassner, E.; Lipp, W.: Wirklichkeitsgetreue Lebensdauerfunktion für Fahrzeugbauteile. In: Beispiele angewandter Forschung, Jahrbuch der Fraunhofer-Gesellschaft, München, S. 63-69 (1963)
- Gassner, E.: Bericht über die in der Bundesrepublik Deutschland durchgeführten Untersuchungen auf dem Gebiet der Ermüdungsfestigkeit im Flugzeugbau. In: Minutes of the 10th ICAF-AGARD-Symposium Rome, April 1963
- Gassner, E.; Jacoby, G.: Betriebsfestigkeit zur Ermittlung zulässiger Entwurfsspannungen für die Flügelunterseite eines Transportflugzeuges Luftfahrttechnik-Raumfahrttechnik 9, Nr. 1, S.6-19 (1964)
- Schutz, W.: Sichere und wirtschaftliche Konstruktionen durch Betriebsfestigkeitsversuche Landtechnische Forschung 14, Nr. 1, S.20-24 (1964)
- Schweer, W.: Beanspruchungskollektive als Bemessungsgrundlage für Hüttenwerkslaufkrane Stahl und Eisen 84, Nr. 3, S.138-53 (1964)
- Gassner, E.; Griesse, F.W.; Haibach, E.: Ertragbare Spannungen und Lebensdauer einer Schweissverbindung aus St37 bei verschiedenen Formen des Beanspruchungskollektivs. Archiv für das Eisenhüttenwesen 35, Nr. 3, S.255-267 (1964)
- Gassner, E.; Wegner, W.: Zur Tragwerks-Betriebsfestigkeit des Geschäftsflugzeuges "HFB 320 Hansa". In: Jahrbuch 1963 der WGLR, S. 314-322
- Haibach, E.: Zeitfestigkeit und Betriebsfestigkeit von Titanwerkstoffen im Vergleich zu Stählen und Leichtmetallen. Materialprüfung 7 (1965) Nr. 4, S. 118-22
- Schutz, W.: Bemessungsspannung und Lebensdauer für Flugzeugbauteile aus Stahl. 1.7704.6, Nr. FB-51. DM 28,50

Anon.: Zur Tragwerks-Betriebsfestigkeit des Geschäftsflugzeuges "HFB 320 Hansa", LBF Rpt. Nr. F48

Anon.: Betriebsfestigkeit und Zeitfestigkeit gebohrter Flachstabe aus dem Cr-Mo-V-Stahl 1.7704.6, LBF Rpt. TM 8/64

Anon.: Betriebsfestigkeit geschweisster Rohrverbindungen aus Chrom-Molybdan-Stahl 1.7214.6, LBF Rpt. TM 11/64

Anon.: Einfluss des Hartverchromens auf die Zeit- und Betriebsfestigkeit eines niedriglegierten Vergutungsstahles mit einer Zugfestigkeit von 200 kp/mm²
LBF Rpt. TM 12/65

Anon.: Betriebsfestigkeit von Augenstaben aus einer Aluminiumlegierung (Luftfahrtwerkstoff 3.1245.7). LBF Rpt. TM 14/65